SuperLite® SL551400-100 (3.0mm)

Polypropylene

Azdel, Inc.

Message:

AZDEL SuperLite SL551400-100 (3.0mm) is a low pressure, thermoformable, thermoplastic composite of polypropylene and long chopped glass fibers. Usually combined with outer layers as needed for the application (i.e.; adhesive films, barrier films, scrim, tough PP films, non-wovens, reinforcements or just the bare surface.) Typically used in non-structural applications where a very high strength to weight ratio is required, such as automotive headliners, door panels, package shelves, and other interior trim.

| General Information | | | |
|---------------------------|--|-------|-------------|
| Filler / Reinforcement | Long glass fiber, 55% filler by weight | | |
| Appearance | Black | | |
| | Natural color | | |
| Forms | Sheet | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 0.519 | g/cm³ | ASTM D792 |
| Molding Shrinkage - Flow | < 0.020 | % | ASTM D955 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Modulus | 3300 | MPa | ASTM D638 |
| Tensile Strength | 34.0 | MPa | ASTM D638 |
| Impact | Nominal Value | Unit | Test Method |
| Instrumented Dart Impact | | | ASTM D3763 |
| 23°C, Energy at Peak Load | 4.50 | J | ASTM D3763 |
| 23°C, Total Energy | 7.60 | J | ASTM D3763 |
| Additional Information | | | |

Multi-axial Impact Peak Force, ASTM D3763, 23°C: 970 NMass per unit area, Internal Test Method: 1400 g/m²Flexual Strength, SAE J949: 20 MPaFlexual Modulus, SAE J949: 1300 MPa

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

