# Lotrène® LLDPE Q1018M

## Linear Low Density Polyethylene

### **QATOFIN** Company Limited

#### Message:

Lotrène ® Q1018 Series are Linear Low Density Polyethylene resins produced in a gas phase reactor using butene (C4) co-monomer.

They are designed for blown film applications and can be used in pure form as well as blended with other PE resins, such as LDPE or HDPE and mPE resins for mono extrusion or co-extrusion process to modify film properties.

Lotrène © Q1018 Series are suited for many applications in the field of consumer, agricultural, industrial, food or hygiene packaging, for example: collation shrink, liners, FFS bags, heavy duty sacks,

refuse, tunnel films, mulching films…

General Information				
Additive	Erucamide Lubricating Additive (1000 ppm) Anti-caking agent (3200 ppm)			
	heat stabilizer			
Features	Butene comonomer			
	smoothness			
	Anti-caking property			
	Thermal Stability			
Uses	Packaging			
	Thin wall packaging			
	Films			
	Lining			
	Bags			
	Industrial application			
	Mixing			
	Agricultural application			
	Shrinkable film			
	Consumer goods application field			
	Heavy packing bag			
Processing Method	Film extrusion			
	Blow film			
	Co-extruded film			
Physical	Nominal Value	Unit	Test Method	
Specific Gravity	0.918	g/cm <sup>3</sup>	ASTM D792	
Melt Mass-Flow Rate (MFR) (190°C/2.16				
kg)	1.0	g/10 min	ASTM D1238	

Films	Nominal Value	Unit	Test Method
secant modulus			ASTM D882
1% secant, MD: 40 µm, blown film	215	MPa	ASTM D882
1% secant, TD: 40 µm, blown film	245	MPa	ASTM D882
Tensile Strength			ASTM D882
MD: Yield, 40 µm, blown film	11.0	MPa	ASTM D882
TD: Yield, 40 μm, blown film	11.0	MPa	ASTM D882
MD: Broken, 40 µm, blown film	38.0	MPa	ASTM D882
TD: Broken, 40 µm, blown film	33.0	MPa	ASTM D882
Tensile Elongation			ASTM D882
MD: Broken, 40 µm, blown film	800	%	ASTM D882
TD: Broken, 40 µm, blown film	850	%	ASTM D882
Dart Drop Impact <sup>1</sup> (40 µm, Blown Film)	150	g	ASTM D1709
Elmendorf Tear Strength			ASTM D1922
MD: 40 µm, blown film	280	g	ASTM D1922
TD: 40 µm, blown film	480	g	ASTM D1922
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	100	°C	ASTM D1525
Peak Crystallization Temperature (DSC)	122	°C	Internal method
Optical	Nominal Value	Unit	Test Method
Gloss (45°, 40.0 μm, Blown Film)	60		ASTM D2457
Haze (40.0 µm, Blown Film)	11	%	ASTM D1003
Extrusion	Nominal Value	Unit	
Cylinder Zone 1 Temp.	180 - 220	°C	
Cylinder Zone 2 Temp.	180 - 220	°C	
Cylinder Zone 3 Temp.	180 - 220	°C	
Cylinder Zone 4 Temp.	180 - 220	°C	
Cylinder Zone 5 Temp.	180 - 220	°C	
Melt Temperature	200	°C	
Extrusion instructions			
Blow-up ratio: 2:1 to 3:1Die gap: >1.8 mm			
NOTE			
1	E50		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519 Phone: +86 13424755533 Email: sales@su-jiao.com No. 215, Lianhe North Road, Fengxian District, Shanghai, China

