Geon™ Vinyl Flexible R7661A

Flexible Polyvinyl Chloride

PolyOne Corporation

Message:

Geon™Vinyl Flexible R7661A is a flexible polyvinyl chloride product. It can be processed by extrusion coating and is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific. Typical application areas are: wire and cable.

Features include:

Flame Retardant

Stable

| General Information | | | |
|---|-----------------------------------|---------|-------------|
| Additive | Lead stabilizer | | |
| Features | Flame retardancy | | |
| Uses | Building wire insulation material | | |
| | Wire and cable applications | | |
| | | | |
| Wire Types | TW | | |
| Forms | Particle | | |
| Processing Method | Extrusion coating | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 1.32 | g/cm³ | ASTM D792 |
| Hardness | Nominal Value | Unit | Test Method |
| Durometer Hardness (Shore A, 15 sec) | 83 | | ASTM D2240 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength ¹ (Yield) | 18.6 | MPa | ASTM D638 |
| Tensile Elongation ² (Break) | 350 | % | ASTM D638 |
| Aging | Nominal Value | Unit | |
| Tensile strength retention rate ³ (121°C, 1.91 mm) | 100 | % | |
| Elongation retention rate ⁴ (121°C, 1.91 mm) | 75 | % | |
| Thermal | Nominal Value | Unit | Test Method |
| Brittleness Temperature | -25.0 | °C | ASTM D746 |
| Electrical | Nominal Value | Unit | Test Method |
| Volume Resistivity | 5.4E+15 | ohms·cm | ASTM D257 |
| Flammability | Nominal Value | Unit | Test Method |
| Oxygen Index (1.91 mm) | 24 | % | ASTM D2863 |
| Additional Information | | | |
| 注释:模制厚板(0.075")的典型属性;不能视为 | 技术规格. | | |
| Extrusion | Nominal Value | Unit | |
| Melt Temperature | 165 - 175 | °C | |
| NOTE | | | |

| 1. | Type 4, 510mm/min |
|----|------------------------|
| 2. | Type 4, 510mm/min |
| 3. | 336 hours, UL standard |
| 4. | 336 hours, UL standard |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

