

DynaPath™ 3125-SS

Polyether Imide

Polymer Dynamix

Message:

Static Dissipative Polyetherimid

Features:

Radio Frequency Shielding (RFI)

Electromagnetic Shielding (EMI)

Sloughing, Non

Excellent Processability

Applications:

Automotive

Industrial

Electrical/Electronic Applications

General Information	
Features	Electromagnetic Shielding (EMI)
	Good Processability
	Non-Sloughing
	Radio Frequency Shielding (RFI)
Uses	Automotive Applications
	Electrical/Electronic Applications
	Industrial Applications
	Radiation Shielding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.48	g/cm ³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	103	MPa	ASTM D638
Tensile Elongation (Break)	5.5	%	ASTM D638
Flexural Modulus	3100	MPa	ASTM D790
Flexural Strength	138	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	27	J/m	ASTM D256
Unnotched Izod Impact (23°C, 3.18 mm)	270	J/m	ASTM D256
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	< 1.0E+2	ohms	ASTM D257
Volume Resistivity	< 10	ohms · cm	ASTM D257

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

