

ESTACARB 2060 V0 HF

Polycarbonate

Cossa Polimeri S.r.l.

Message:

ESTACARB 2060 V0 HF is a Polycarbonate (PC) product. It is available in Europe. Applications of ESTACARB 2060 V0 HF include electrical/electronic applications and engineering/industrial parts.

Characteristics include:

Flame Rated

Halogen Free

Flame Retardant

Good Processability

Good UV Resistance

General Information			
Features	Antimony Free Bromine Free Chlorine Free Flame Retardant Good Flow Good Processability Good UV Resistance High Heat Resistance High Impact Resistance		
Uses	Electrical Parts Electrical/Electronic Applications Engineering Parts		
Appearance	Opaque		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	20	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.50 to 0.70	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield	65.0	MPa	
Break	60.0	MPa	
Tensile Elongation (Break)	> 50	%	ASTM D638
Flexural Modulus	2500	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256

0°C	450	J/m	
23°C	500	J/m	
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature			
--	148	°C	ASTM D1525 ¹
--	145	°C	ASTM D1525 ²
Ball Indentation Temperature	135	°C	IEC 60335-1
Flammability	Nominal Value	Unit	Test Method
Flame Rating			
1.60 mm	V-0		UL 94
3.20 mm	V-0		
Glow Wire Ignition Temperature (2.00 mm)	960	°C	IEC 60695-2-13
NOTE			
1.	Rate A (50°C/h), Loading 1 (10 N)		
2.	Rate A (50°C/h), Loading 2 (50 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

