

Andur 8-5 APLS

Polyurethane (Polyester, TDI)
Anderson Development Company

Message:

Andur 8-5APLS is a polyester based, toluene diisocyanate terminated prepolymer designed for optimum solvent resistance. Elastomers with a Shore A durometer hardness of 83-86 can be obtained when Andur 8-5APLS is cured with Curene 442 [4,4'-methylene-bis (orthochloroaniline)]. Elastomers of 53-56 Shore A durometer hardness can be obtained when cured with Curene 49.

General Information			
Forms	Liquid		
Thermoset	Nominal Value	Unit	Test Method
Thermoset Mix Viscosity (100°C)	1100	cP	ASTM D2393
Additional Information			
NCO: 3.2 to 3.6%			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT