

LNP™ STAT-KON™ JX89626 compound

Polyethersulfone

SABIC Innovative Plastics

Message:

LNP STAT-KON JX89626 is a compound based on Polyethersulfone containing Proprietary Fillers. Added feature of this material is: Electrically Conductive.

Also known as: LNP* STAT-KON* Compound PDX-J-89626

Product reorder name: JX89626

General Information			
Filler / Reinforcement	Proprietary		
Features	Electrically Conductive		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.41	g/cm ³	ASTM D792
Molding Shrinkage			ASTM D955
Flow : 24 hr	0.10 to 0.30	%	
Across Flow : 24 hr	0.50 to 0.80	%	
Water Absorption			
24 hr, 50% RH	0.49	%	ASTM D570
Equilibrium, 23°C, 50% RH	0.71	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	11900	MPa	ASTM D638
--	11200	MPa	ISO 527-2/1
Tensile Strength			
Break ²	163	MPa	ASTM D638
Break	161	MPa	ISO 527-2/5
Tensile Elongation			
Break ³	2.1	%	ASTM D638
Break	2.2	%	ISO 527-2/5
Flexural Modulus			
50.0 mm Span ⁴	10100	MPa	ASTM D790
-- ⁵	9680	MPa	ISO 178
Flexural Stress			
--	226	MPa	ISO 178
Break, 50.0 mm Span ⁶	238	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	49	J/m	ASTM D256
23°C ⁷	6.1	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			

23°C	600	J/m	ASTM D4812
23°C ⁸	37	kJ/m ²	ISO 180/1U
Instrumented Dart Impact			
23°C, Total Energy	7.30	J	ASTM D3763
--	3.80	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed, 3.20 mm	220	°C	ASTM D648
0.45 MPa, Unannealed, 64.0 mm Span ⁹	219	°C	ISO 75-2/Bf
1.8 MPa, Unannealed, 3.20 mm	214	°C	ASTM D648
1.8 MPa, Unannealed, 64.0 mm Span ¹⁰	214	°C	ISO 75-2/Af
CLTE			ASTM D696
Flow : -30 to 30°C	4.7E-5	cm/cm/°C	
Transverse : -30 to 30°C	3.8E-5	cm/cm/°C	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	2.0 to 5.0	ohms	ASTM D257
Injection	Nominal Value	Unit	
Drying Temperature	121 to 149	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.050	%	
Rear Temperature	343 to 354	°C	
Middle Temperature	360 to 371	°C	
Front Temperature	371 to 382	°C	
Processing (Melt) Temp	354 to 371	°C	
Mold Temperature	138 to 149	°C	
Back Pressure	0.344 to 0.689	MPa	
Screw Speed	60 to 100	rpm	
NOTE			
1.	50 mm/min		
2.	Type I, 5.0 mm/min		
3.	Type I, 5.0 mm/min		
4.	1.3 mm/min		
5.	2.0 mm/min		
6.	1.3 mm/min		
7.	80*10*4		
8.	80*10*4		
9.	80*10*4 mm		
10.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

