

# Manner Flexible PVC V924 NAT601

Flexible Polyvinyl Chloride

Manner Plastics, L.P.

## Message:

Recommended Applications: 105°C Insulation and Jacket Compound designed for use in CL2R, CL3R applications. This product complies with the European Union Restriction on Hazardous Substances (RoHS) directive.

General Information			
Uses	Insulation		
	Wire & Cable Applications		
Appearance	Natural Color		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.33 to 1.37	g/cm <sup>3</sup>	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore C, 15 sec)	65 to 71		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	19.0	MPa	ASTM D638
Tensile Elongation (Break)	350	%	ASTM D638
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	35	%	ASTM D2863
Additional Information	Nominal Value	Unit	
Stock Temperature - Recommended Molding	188	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT