

Next Nylon 66 Industrial Series PG30-02BK

Polyamide 66

Next Polymers Ltd.

Message:

Description

PA66 Glass Fiber Reinforced Black Compound

Product Applications

This grade is commonly used in the automotive industries for engine components such as water tanks, degassing and liquid containers, engine covers, various housing and component of electric tools.

Benefits

Excellent combination between Thermal and Mechanical properties.

General Information				
Filler / Reinforcement		Glass fiber reinforced material, 30% filler by weight		
Uses		Protective cover		
		Parts under the hood of a car		
		Application in Automobile Field		
		Container		
		Shell		
Agency Ratings		EC 1907/2006 (REACH)		
RoHS Compliance		RoHS compliance		
Appearance		Black		
Processing Method		Injection molding		
Physical	Dry	Conditioned	Unit	Test Method
Specific Gravity	1.36	--	g/cm ³	ASTM D792
Molding Shrinkage				ASTM D955
Flow	0.35	--	%	ASTM D955
Transverse flow	0.88	--	%	ASTM D955
Water Absorption				ASTM D570
23°C, 24 hr	2.1	--	%	ASTM D570
Saturation ¹	6.5	--	%	ASTM D570
Hardness	Dry	Conditioned	Unit	Test Method
Rockwell Hardness				ASTM D785
Class m	110	--		ASTM D785
Class r	120	--		ASTM D785
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Strength	140	100	MPa	ASTM D638
Tensile Elongation (Break)	4.0	6.0	%	ASTM D638
Flexural Modulus	9500	7500	MPa	ASTM D790
Flexural Strength	230	200	MPa	ASTM D790
Impact	Dry	Conditioned	Unit	Test Method

Notched Izod Impact (23°C)	110	160	J/m	ASTM D256
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				ASTM D648
0.45 MPa, not annealed	258	--	°C	ASTM D648
1.8 MPa, not annealed	245	--	°C	ASTM D648
Melting Temperature	262	--	°C	ASTM D2117
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+14	--	ohms	IEC 60093
Volume Resistivity	1.0E+15	1.0E+15	ohms·cm	IEC 60093
Dielectric Strength	26	24	kV/mm	IEC 60243-1
Comparative Tracking Index	650	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (0.800 mm)	HB	--		UL 94
Additional Information				

干燥
This grade is not suitable for food contact, medical devices or toy applications

Injection	Dry	Unit	
Drying Temperature - Hot Air Dryer	80.0		°C
Drying Time	4.0 - 6.0		hr
Suggested Max Moisture	0.20		%
Rear Temperature	260 - 270		°C
Middle Temperature	270 - 280		°C
Front Temperature	280 - 290		°C
Mold Temperature	65.0 - 85.0		°C

NOTE

1. Immersed

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
 Phone: +86 13424755533
 Email: sales@su-jiao.com
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT