

ECO-FLEX™ SA-55A

Thermoplastic Vulcanizate, Rubber Based

SYNESIS LLC

Message:

ECO-FLEX™ SA-55A is a Thermoplastic Vulcanizate, Rubber Based (RTPV) product. It is available in North America. Applications of ECO-FLEX™ SA-55A include additive/masterbatch, automotive, consumer goods and sheet. Primary characteristic: eco-friendly/green.

General Information			
Recycled Content	Yes		
Uses	Automotive Applications		
	Blending		
	Consumer Applications		
	Sheet		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	1.03	g/cm ³	ISO 1183/A
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore A, 15 sec)	55		ISO 868
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ¹ (100% Strain)	1.70	MPa	ISO 37
Tensile Stress ² (Yield)	2.80	MPa	ISO 37
Tensile Elongation ³ (Break)	440	%	ISO 37
Tear Strength ⁴	17	kN/m	ISO 34-1
Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength in Air (100°C, 1008 hr)	8.0	%	ISO 188
Change in Tensile Strain at Break in Air (100°C, 1008 hr)	8.0	%	ISO 188
Change in Shore Hardness in Air (100°C, 1008 hr)	2.0		ISO 188
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-40.0	°C	ISO 812
Flammability	Nominal Value	Unit	Test Method
Burning Rate	44	mm/min	SAE J369
Additional Information	Nominal Value		Test Method
Ozone Resistance ⁵	Pass - No Cracking		ISO 1431-1
NOTE			
1.	Type 1, 50 mm/min		
2.	Type 1, 50 mm/min		
3.	Type 1, 50 mm/min		

4.	Method Bb, Angle (Nicked), 50 mm/min
5.	Procedure A, 20% Elongation, 51 MPa

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

