

RTP 385 TFE 20

Polycarbonate
RTP Company

Message:

Warning: The status of this material is 'Commercial: Limited Issue'
The data for this material has not been recently verified.
Please contact RTP Company for current information prior to specifying this grade.

General Information			
Filler / Reinforcement	Carbon fiber reinforced material, 30% filler by weight		
Additive	PTFE lubricant (20%)		
Features	Lubrication		
RoHS Compliance	Contact manufacturer		
Appearance	Black		
	Natural color		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.45	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.050	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.060	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	19300	MPa	ASTM D638
Tensile Strength	152	MPa	ASTM D638
Tensile Elongation (Break)	2.5	%	ASTM D638
Flexural Modulus	17900	MPa	ASTM D790
Flexural Strength	241	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.18 mm)	160	J/m	ASTM D256
Unnotched Izod Impact (3.18 mm)	850	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	149	°C	ASTM D648
1.8 MPa, not annealed	143	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+4	ohms · cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.59 mm)	HB		UL 94
Additional Information			
The value listed as Flammability, UL 94, was tested in accordance with RTP test standards.Tensile Elongation, ASTM D-638: 2-3%			
Injection	Nominal Value	Unit	

Rear Temperature	260 - 316	°C
Middle Temperature	260 - 316	°C
Front Temperature	260 - 316	°C
Mold Temperature	65.6 - 121	°C
Injection Pressure	103 - 138	MPa

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

