

Nypol® PA A3 T20 PRTA011 NR389

Polyamide 66

Petropol Industry and Trade of Polymers LTDA

Message:

Polyamide 6.6 in color black with 20% of mineral reinforced. Ideal for injection molding, good set of thermal properties, electrical and mechanical.

General Information			
Filler / Reinforcement	Mineral,20% Filler by Weight		
Appearance	Black		
Processing Method	Injection Molding		
Resin ID (ISO 1043)	>PA 6.6 MD20<		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.25	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.80 to 1.1	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	78.5	MPa	ASTM D638
Tensile Elongation (Break)	10	%	ASTM D638
Flexural Modulus	3820	MPa	ASTM D790
Flexural Strength	113	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	49	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	175	°C	ASTM D648
Peak Melting Temperature	250 to 265	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+13 to 1.0E+15	ohms·cm	ASTM D257
Dielectric Strength	3.5	kV/mm	ASTM D149
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.20	%	
Processing (Melt) Temp	260 to 280	°C	
Mold Temperature	80.0 to 100	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

