Petrothene® GS710061

Linear Low Density Polyethylene LyondellBasell Industries

Message:

The PETROTHENE SELECT series of resins are pelletized, high performance hexene, linear low density polyethylenes for applications requiring superior strength and toughness. These products offer significant improvements in mechanical properties and excellent additive homogeneity without sacrificing processability compared to conventional Hexene LLDPE materials. GS 710 exhibits superior processability compared to competitive High Performance Hexene LLDPE materials. Applications include trash and can liners, commercial and industrial packaging, as well as consumer packaging. The PETROTHENE SELECT series resins offer enhanced film strength, drawdown, toughness and heat seal strength.

General Information			
Additive	Medium Antiblock (12%)		
Features	Food Contact Acceptable		
	Good Drawdown		
	Good Heat Seal		
	Good Processability		
	Good Strength		
	Low Density		
	Ultra High Toughness		
Uses	Consumer Applications		
	Industrial Applications		
	Liners		
	Packaging		
Agency Ratings	FDA 21 CFR 177.1520		
Forms	Pellets		
Processing Method	Film Extrusion		
Physical	Nominal Value	Unit	Test Method
Density	0.924	g/cm³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16	1.0	40 .	ACTI A D4000
kg)	1.0	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	25	μm	
Secant Modulus			ASTM D882
1% Secant, MD : 25 μm, Blown Film	193	MPa	
1% Secant, TD : 25 μm, Blown Film	200	MPa	
Tensile Strength			ASTM D882
MD : Break, 25 µm,Blown Film	55.2	MPa	
TD : Break, 25 µm,Blown Film	41.4	МРа	
Tensile Elongation			ASTM D882
MD : Break, 25 µm,Blown Film	580	%	

TD : Break, 25 µm,Blown Film	720	%	
Dart Drop Impact (25 µm, Blown Film)	600	g	ASTM D1709A
Elmendorf Tear Strength			ASTM D1922
MD : 25 μm, Blown Film	350	g	
TD : 25 µm, Blown Film	580	g	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

