

Diamond PC 1212 FR0 264 BLACK

Polycarbonate
Network Polymers, Inc.

Message:

Diamond PC 1212 FR0 264 BLACK is a Polycarbonate (PC) product. It is available in North America.
Characteristics include:
Flame Rated
Flame Retardant

General Information			
UL YellowCard	E51193-101898833	E51193-101898834	
Additive	Flame Retardant		
Features	Flame Retardant		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.21	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) ¹ (300°C/1.2 kg)	20	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.50 to 0.70	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield, Injection Molded ²	62.1	MPa	
Break, Injection Molded	59.3	MPa	
Flexural Modulus ³	2280	MPa	ASTM D790B
Flexural Strength ⁴ (Yield)	90.3	MPa	ASTM D790B
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.18 mm)	640	J/m	ASTM D256A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed, 3.18 mm	137	°C	
1.8 MPa, Unannealed, 3.18 mm	132	°C	
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
1.50 mm	V-0		
3.00 mm	5VA		
Injection	Nominal Value	Unit	
Drying Temperature - Desiccant Dryer	104 to 116	°C	
Drying Time - Desiccant Dryer	2.0 to 4.0	hr	
Suggested Max Moisture	0.020	%	
Hopper Temperature	249 to 282	°C	
Rear Temperature	260 to 293	°C	
Middle Temperature	260 to 293	°C	

Front Temperature	260 to 293	°C
Nozzle Temperature	260 to 293	°C
Mold Temperature	71.1 to 104	°C
Injection Pressure	82.7 to 103	MPa

NOTE		
1.	Procedure A	
2.	51 mm/min	
3.	Method I (3 point load), 1.3 mm/min	
4.	Method I (3 point load), 1.3 mm/min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT