

KMI PC 101HMB

Polycarbonate

KMI Group Inc.

Message:

KMI PC 101HMB is a Polycarbonate (PC) product. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America. Primary characteristic: flame rated.

General Information			
Uses	General Purpose		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR)	7.0	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	61.8	MPa	ASTM D638
Tensile Elongation (Break)	100	%	ASTM D638
Flexural Modulus	2160	MPa	ASTM D790
Flexural Strength	85.3	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	860	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	135	°C	ASTM D256
CLTE - Flow	7.0E-5	cm/cm/°C	ISO 11359-2
Flammability	Nominal Value	Test Method	
Flame Rating	HB	UL 94	
Injection	Nominal Value	Unit	
Drying Temperature	120	°C	
Drying Time	4.0 to 8.0	hr	
Processing (Melt) Temp	270 to 300	°C	
Mold Temperature	70.0 to 100	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT