

# Kaneka MUH E7301

Acrylonitrile Butadiene Styrene

Kaneka Corporation

## Message:

Kaneka MUH E7301 is an acrylonitrile butadiene styrene (ABS) material. This product is available in North America and is processed by injection molding. The main features of Kaneka MUH E7301 are:

- high liquidity
- Good processability
- Impact resistance
- Heat resistance

Typical application areas include:

- Electrical/electronic applications
- Automotive Industry

General Information			
Features	Impact resistance, good		
	Good formability		
	High liquidity		
	Heat resistance, high		
Uses	Electrical/Electronic Applications		
	Application in Automobile Field		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.07	g/cm <sup>3</sup>	ASTM D792
Molding Shrinkage - Flow	0.50 - 0.80	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	48.0	MPa	ASTM D638
Tensile Elongation (Break)	13	%	ASTM D638
Flexural Modulus	2400	MPa	ASTM D790
Flexural Strength	73.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (6.40 mm)	98	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	110	°C	ASTM D648
Additional Information			
Spiral Flow, Kaneka Method, 482°F, 3 mm: 24.2 in			
Injection	Nominal Value	Unit	
Drying Temperature	100	°C	
Drying Time	3.0	hr	

Rear Temperature	240 - 260	°C
Middle Temperature	240 - 260	°C
Front Temperature	240 - 260	°C
Processing (Melt) Temp	280	°C
Mold Temperature	50.0	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT