# **ISOTHANE® 3085AF**

### Thermoplastic Polyurethane Elastomer (Polyether)

Great Eastern Resins Industrial Co Ltd (GRECO)

#### Message:

ISOTHANE 3085AF product is an 85A, polyether based thermoplastic Polyurethanes. It exhibits excellent hydrolytic resistance, fungus resistance and low temperature performance properties. It can be injection molded, blow molded, and extruded.

General Information				
Features	Fungus Resistant			
	Good Thermal Stability			
	Hydrolysis Resistant			
Uses	Belts/Belt Repair			
	Conveyor Parts			
	Film			
	Sheet			
	Tubing			
Processing Method	Blow Molding			
	Extrusion			
	Injection Molding			
Physical	Nominal Value	Unit	Test Method	
Specific Gravity	1.13	g/cm³	ASTM D792	
Hardness	Nominal Value	Unit	Test Method	
Durometer Hardness (Shore A)	85		ASTM D2240	
Mechanical	Nominal Value	Unit	Test Method	
Taber Abrasion Resistance (H-22 Wheel)	20.0	mg	ASTM D1044	
Elastomers	Nominal Value	Unit	Test Method	
Tensile Stress			ASTM D412	
50% Strain	4.50	MPa		
100% Strain	5.90	MPa		
300% Strain	12.0	MPa		
Tensile Strength (Yield)	36.0	MPa	ASTM D412	
Tensile Elongation (Break)	600	%	ASTM D412	
Tear Strength <sup>1</sup>	110	kN/m	ASTM D624	
Compression Set			ASTM D395B	
23°C, 22 hr	30	%		
70°C, 22 hr	35	%		
Extrusion	Nominal Value	Unit		

Drying Temperature	93.0	°C	
Cylinder Zone 1 Temp.	182 to 193	°C	
Cylinder Zone 2 Temp.	188 to 199	°C	
Cylinder Zone 3 Temp.	193 to 204	°C	
Adapter Temperature	193 to 204	°C	
Die Temperature	193 to 210	°C	
NOTE			
1.	Die C		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

