

Polifor® 5000/V2-EP NATURALE

Polypropylene Copolymer

SO.F.TER. SPA

Message:

Polypropylene copolymer, flame retardant grade UL94 V-2, low halogen content and PBDE free

General Information			
UL YellowCard	E187982-227090		
Features	Copolymer		
	Flame Retardant		
	Halogen Free		
Uses	Appliances		
	Automotive Applications		
Agency Ratings	EC 1907/2006 (REACH)		
UL File Number	E187982		
Appearance	Natural Color		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.930	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	12	g/10 min	ASTM D1238
Molding Shrinkage	1.6	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	27.0	MPa	ASTM D638
Tensile Elongation (Break)	50	%	ASTM D638
Flexural Modulus	1200	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
0°C	35	J/m	
23°C	70	J/m	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	45.0	°C	ASTM D648
Vicat Softening Temperature	70.0	°C	ASTM D1525 ¹
Ball Pressure Test (125°C)	Pass		IEC 335
Electrical	Nominal Value	Unit	Test Method
Needle Flame Test	Pass		IEC 60695-11-5
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94

0.800 mm	V-2		
1.60 mm	V-2		
3.20 mm	V-2		
Glow Wire Ignition Temperature	960	°C	IEC 60695-2-13
Oxygen Index	23	%	ASTM D2863
Injection	Nominal Value	Unit	
Drying Temperature	60.0	°C	
Drying Time	2.0	hr	
Rear Temperature	180	°C	
Middle Temperature	190	°C	
Front Temperature	200	°C	
Mold Temperature	20.0 to 40.0	°C	
NOTE			

1. Rate A (50°C/h), Loading 2 (50 N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
 Phone: +86 13424755533
 Email: sales@su-jiao.com
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT