# Sumiliteresin® PR-1095 I

## Phenolic

### SBHPP

#### Message:

SUMILITERESIN® PR-1095 I is a modified Tall oil novolak phenolic resin.

Characteristics

SUMILITERESIN<sup>®</sup> PR-1095 I is a powder novolac phenolic resin which modified high Tall Oil, hexamine content about 7%. For Friction Material : improve flexibility, friction coefficient and good feeling of braking. For Rubber Reinforcing : Low money viscosity, easy mixture, improve flexibility and preferable for SBR compound.

General Information		
Features	Low viscosity	
	Good flexibility	
Appearance	Brown	
Forms	Powder	
Physical	Nominal Value	Unit
Flow Length (125°C)	3.50 - 5.00	cm
Sieve Analysis - 150µm		%
Thermal	Nominal Value	Unit
Melting Temperature	80.0 - 90.0	°C
Uncured Properties	Nominal Value	Unit
Gel Time (165°C)	0.33 - 0.58	min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

