

UNIVAL™ DMDA-6220 NT 7

High Density Polyethylene Resin

The Dow Chemical Company

Message:

Excellent stress crack resistance and rigidity

High impact strength

Moderate swell

High melt strength

Complies with:

U.S. FDA 21 CFR 177.1520 (c) 3.2a

Canadian HPFB No Objection (with limitations)

EU, No 10/2011

Consult the regulations for complete details.

UNIVAL™ DMDA-6220 NT 7 High Density Polyethylene (HDPE) Resin is an antistat containing, multipurpose polymer designed for the high speed production of blow molded containers used to package household industrial chemicals (e.g., detergents, bleach, fabric softeners), toiletries and cosmetics (e.g., shampoos, creams, lotions, etc.), health and medicinal aids, and food products. In addition, it can be blow molded into other thin walled parts and houseware items, and also can be extruded into profiles.

General Information			
UL YellowCard	E337483-100635872		
Agency Ratings	FDA 21 CFR 177.1520(c) 3.2a		
	HPFB (Canada) No Objection 3		
	Europe No 10/2011		
Forms	Particle		
Processing Method	Blow molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.953	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR)			ASTM D1238
190°C/2.16 kg	0.38	g/10 min	ASTM D1238
190°C/21.6 kg	33	g/10 min	ASTM D1238
Environmental Stress-Cracking Resistance (50°C, 100% Igepal, F50)	60.0	hr	ASTM D1693
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	62		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield	26.9	MPa	ASTM D638
Fracture	31.7	MPa	ASTM D638
Tensile Elongation			ASTM D638
Yield	7.0	%	ASTM D638
Fracture	1000	%	ASTM D638
Flexural Modulus - 2% Secant	1050	MPa	ASTM D790B
Impact	Nominal Value	Unit	Test Method

Tensile Impact Strength ¹	168	kJ/m ²	ASTM D1822
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	67.0	°C	ASTM D648
Brittleness Temperature	< -76.1	°C	ASTM D746
Vicat Softening Temperature	129	°C	ASTM D1525
Melting Temperature (DSC)	131	°C	Internal method
Peak Crystallization Temperature (DSC)	119	°C	Internal method
Additional Information			
根据 ASTM D 4976 进行基板模制和测试.			
NOTE			

1. Type s

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

