# Daelim Po1y® LL-04SUV

Linear Low Density Polyethylene DAELIM INDUSTRIAL CO., LTD.

## Message:

Daelim Po1y®LL-04SUV is a linear low density polyethylene product, and the filler is glass fiber reinforced material. It is available in the Asia-Pacific region. Daelim Po1y®LL-04SUV application areas include bags/linings, movies and food contact applications.

Features include:

Good processability

Good UV resistance

Transparency

General Information					
Filler / Reinforcement	Glass fiber reinforced material				
Features	Good UV resistance				
	Workability, good				
	Definition, high				
Uses	Films				
	Bags				
Agency Ratings	ASTM D 1248, I, Class A, Cat. 4				
	FDA 21 CFR 177.1520				
Forms	Particle				
Physical	Nominal Value	Unit	Test Method		
Density	0.923	g/cm³	ASTM D1505		
Melt Mass-Flow Rate (MFR) (190°C/2 kg)	2.16 1.1	g/10 min	ASTM D1238		
Films	Nominal Value	Unit	Test Method		
Film Thickness - Tested	25	μm			
Tensile Strength			ASTM D882		
MD: Yield	12.7	MPa	ASTM D882		
TD: Yield	11.8	MPa	ASTM D882		
MD: Fracture	40.2	MPa	ASTM D882		
TD: Fracture	31.4	MPa	ASTM D882		
Tensile Elongation			ASTM D882		
MD: Fracture	550	%	ASTM D882		
TD: Fracture	700	%	ASTM D882		
Dart Drop Impact	100	g	ASTM D1709		
Elmendorf Tear Strength			ASTM D1922		
MD	3.0	g	ASTM D1922		
TD	10	g	ASTM D1922		

Optical	Nominal Value	Unit	Test Method
Haze	10	%	ASTM D1003

#### Additional Information

Tear Strength, MD, ASTM D-1004: 110kg/cmTear Strength, TD, ASTM D-1004: 100kg/cm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

### Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

