

LNP™ THERMOCOMP™ RF006LXP compound

Polyamide 66

SABIC Innovative Plastics Asia Pacific

Message:

LNP THERMOCOMP RF006LXP is a compound based on Nylon 66 resin containing 30% Glass Fiber. Added features of this material include: Low Extractible.
Also known as: LNP* THERMOCOMP* Compound RF-1006 LE
Product reorder name: RF006LXP

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 30% filler by weight		
Features	Low extract		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.59	g/cm ³	ASTM D792
Molding Shrinkage - Flow (24 hr)	0.40	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹	10500	MPa	ASTM D638
Tensile Strength (Break)	157	MPa	ASTM D638
Tensile Elongation (Break)	2.4	%	ASTM D638
Flexural Modulus	8740	MPa	ASTM D790
Flexural Strength	221	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	80	J/m	ASTM D256
Unnotched Izod Impact (23°C)	750	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 3.20 mm)	246	°C	ASTM D648
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.15 - 0.25	%	
Rear Temperature	266 - 277	°C	
Middle Temperature	282 - 293	°C	
Front Temperature	293 - 304	°C	
Processing (Melt) Temp	282 - 304	°C	
Mold Temperature	93.3 - 110	°C	
Back Pressure	0.172 - 0.344	MPa	
Screw Speed	30 - 60	rpm	
NOTE			
1.	50 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

