

# Globalene® SJ3003

Polypropylene Alloy

Lee Chang Yung Chemical Industry Corp.

Message:

Globalene® SJ3003 is a Polypropylene Alloy (PP Alloy) material. It is available in Asia Pacific or North America for injection molding.

Important attributes of Globalene® SJ3003 are:

Flame Rated

RoHS Compliant

Good Processability

Impact Resistant

Typical applications include:

Appliances

Electrical/Electronic Applications

Household Applications

General Information			
UL YellowCard	E85783-251839	E85783-251846	
Features	Good Moldability		
	High Impact Resistance		
Uses	Appliances		
	Connectors		
	Household Goods		
RoHS Compliance	RoHS Compliant		
UL File Number	E85783		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.930	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	17	g/10 min	ASTM D1238
Molding Shrinkage - Flow	1.4	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	84		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	25.9	MPa	ASTM D638
Tensile Elongation (Yield)	6.5	%	ASTM D638
Flexural Modulus	1240	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	75	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
RTI Elec	65.0	°C	UL 746


RTI Imp	65.0	°C	UL 746
RTI Str	65.0	°C	UL 746
Heat Deflection Temperature	105	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating	V-2		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
 Phone: +86 13424755533  
 Email: sales@su-jiao.com  
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT