OXPEKK® MG230C

Polyetherketoneketone

Oxford Performance Materials, Inc.

Message:

OXPEKK® MG230C is a Polyetherketoneketone (PEKK) material filled with 30% carbon fiber. It is available in Europe or North America. Typical application of OXPEKK® MG230C: Medical/Healthcare

| General Information | | | |
|---|-----------------------------------|----------|-------------|
| Filler / Reinforcement | Carbon Fiber,30% Filler by Weight | | |
| Uses | Medical/Healthcare Applications | | |
| Forms | Pellets | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 1.43 | g/cm³ | ASTM D792 |
| Molding Shrinkage - Flow | 0.10 | % | ASTM D955 |
| Water Absorption (24 hr) | < 0.030 | % | ASTM D570 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Modulus | 2800 | МРа | ASTM D638 |
| Tensile Strength (Break) | 262 | МРа | ASTM D638 |
| Tensile Elongation (Break) | 1.0 | % | ASTM D638 |
| Flexural Modulus | 2200 | МРа | ASTM D790 |
| Flexural Strength | 291 | МРа | ASTM D790 |
| Compressive Strength | 241 | МРа | ASTM D695 |
| Impact | Nominal Value | Unit | Test Method |
| Notched Izod Impact | 53 | J/m | ASTM D256 |
| Thermal | Nominal Value | Unit | Test Method |
| Deflection Temperature Under Load (1.8 MPa, Unannealed) | 321 | °C | ASTM D648 |
| Glass Transition Temperature | 163 | °C | DSC |
| Melting Temperature | 360 | °C | DSC |
| CLTE - Flow | 1.0E-5 | cm/cm/°C | ASTM D696 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

