

VAMPLLEN 2528 V0 CB

Polypropylene

Vamp Tech

Message:

UL 94 V0, 25% glass fiber reinforced, chemically bonded, halogen free, high rigidity and thermal resistance, RoHS.

General Information			
UL YellowCard	E140692-101142178		
Filler / Reinforcement	Glass Fiber,25% Filler by Weight		
Features	Chemically Coupled Halogen Free High Heat Resistance High Rigidity		
RoHS Compliance	RoHS Compliant		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.23	g/cm ³	ASTM D792
Molding Shrinkage			ASTM D955
Flow	0.40	%	
Across Flow	0.90	%	
Water Absorption (Saturation)	0.020	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	6000	MPa	ASTM D638
Tensile Strength (Yield)	60.0	MPa	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength	10	kJ/m ²	ISO 180/A
Unnotched Izod Impact Strength	30	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	145	°C	ASTM D648A
Vicat Softening Temperature	125	°C	ASTM D1525 ¹
RTI Elec	120	°C	UL 746
RTI Imp	120	°C	UL 746
RTI Str	120	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.60 mm	V-0		

3.20 mm	V-0		
Glow Wire Flammability Index (1.00 to 2.00 mm)	850	°C	IEC 60695-2-12
Glow Wire Ignition Temperature (1.00 to 2.00 mm)	775	°C	IEC 60695-2-13
Injection	Nominal Value	Unit	
Drying Temperature	70.0	°C	
Drying Time	3.0	hr	
Processing (Melt) Temp	210	°C	
Mold Temperature	60.0	°C	
NOTE			

1. Loading 2 (50 N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

