Braskem PP HP 427J

Polypropylene Homopolymer

Braskem

Message:

HP 427J is a low fluidity homopolymer with good processability. The product is suitable for both as monolayer and coextruded structures. It does not contain any slip or anti-blocking agents.

Applications:

BOPP films with greater retention in treatment over the metallized layer.

Processing:

Bioriented Film (BOPP)

| General Information | | | |
|--|--------------------------|----------|-------------|
| Features | Good Processability | | |
| | Homopolymer | | |
| | Low Flow | | |
| | | | |
| Uses | Film | | |
| Agency Ratings | FDA 21 CFR 177.1520 | | |
| Processing Method | Bi-axially Oriented Film | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 0.905 | g/cm³ | ASTM D792 |
| Melt Mass-Flow Rate (MFR) (230°C/2.16 | | | |
| kg) | 3.0 | g/10 min | ASTM D1238 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength (Yield, Injection Molded) | 33.0 | МРа | ASTM D638 |
| Tensile Elongation (Yield, Injection | | | |
| Molded) | 9.0 | % | ASTM D638 |
| Flexural Modulus - 1% Secant (Injection | | | |
| Molded) | 1400 | MPa | ASTM D790 |
| Impact | Nominal Value | Unit | Test Method |
| Notched Izod Impact (23°C, Injection | | | |
| Molded) | 35 | J/m | ASTM D256 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

