

GELOY™ EXGY0058 resin

Acrylonitrile Styrene Acrylate + PC
SABIC Innovative Plastics

Message:
Improved ASA/PC blend for high flow, 1.0mm V0 applications. Improved UV performance.

General Information			
Features	High Flow		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.18	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (260°C/2.16 kg)	30.0	cm ³ /10min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	2680	MPa	ASTM D638
--	2680	MPa	ISO 527-2/1
Tensile Strength			
Yield ²	60.0	MPa	ASTM D638
Yield ³	65.0	MPa	ASTM D638
Yield	61.0	MPa	ISO 527-2/5
Yield	66.0	MPa	ISO 527-2/50
Break ⁴	49.0	MPa	ASTM D638
Break ⁵	47.0	MPa	ASTM D638
Break	46.0	MPa	ISO 527-2/5
Break	47.0	MPa	ISO 527-2/50
Tensile Elongation			
Yield ⁶	4.0	%	ASTM D638
Yield ⁷	4.0	%	ASTM D638
Yield	4.0	%	ISO 527-2/5, ISO 527-2/50
Break ⁸	58	%	ASTM D638
Break ⁹	31	%	ASTM D638
Break	50	%	ISO 527-2/5
Break	21	%	ISO 527-2/50
Flexural Modulus ¹⁰	2730	MPa	ISO 178
Flexural Stress	97.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ¹¹ (23°C)	13	kJ/m ²	ISO 179/1eA
Notched Izod Impact			
-30°C	90	J/m	ASTM D256

23°C	330	J/m	ASTM D256
0°C ¹²	12	kJ/m ²	ISO 180/1A
23°C ¹³	13	kJ/m ²	ISO 180/1A
Multi-Axial Instrumented Impact Energy	85.0	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ¹⁴			
0.45 MPa, Unannealed, 64.0 mm Span	90.0	°C	ISO 75-2/Bf
1.8 MPa, Unannealed, 64.0 mm Span	81.0	°C	ISO 75-2/Af
Vicat Softening Temperature			
--	96.0	°C	ISO 306/B50
--	98.0	°C	ISO 306/B120
CLTE			
Flow : -40 to 40°C	6.3E-5	cm/cm/°C	
Transverse : -40 to 40°C	6.3E-5	cm/cm/°C	
Flammability	Nominal Value		Test Method
Flame Rating (1.00 mm, Testing by SABIC)	V-0		UL 94
Fill Analysis	Nominal Value	Unit	Test Method
Melt Viscosity (260°C, 1500 sec ⁻¹)	105	Pa · s	ISO 11443
Injection	Nominal Value	Unit	
Drying Temperature	80.0 to 90.0	°C	
Drying Time	2.0 to 4.0	hr	
Suggested Max Moisture	0.020	%	
Hopper Temperature	60.0 to 80.0	°C	
Rear Temperature	200 to 230	°C	
Middle Temperature	220 to 260	°C	
Front Temperature	230 to 270	°C	
Nozzle Temperature	220 to 260	°C	
Processing (Melt) Temp	230 to 270	°C	
Mold Temperature	50.0 to 70.0	°C	
NOTE			
1.	50 mm/min		
2.	Type I, 5.0 mm/min		
3.	Type I, 50 mm/min		
4.	Type I, 5.0 mm/min		
5.	Type I, 50 mm/min		
6.	Type I, 5.0 mm/min		
7.	Type I, 50 mm/min		
8.	Type I, 5.0 mm/min		
9.	Type I, 50 mm/min		
10.	2.0 mm/min		
11.	80*10*4 sp=62mm		
12.	80*10*4		

13.	80*10*4
14.	80*10*4 mm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

