

DJSilicone NE-9330

Silicone

DONGJUE SILICONE (NANJING) CO., LTD

Message:

Character: High tear strength
Application: NE-93 is suitable for products with special tear strength requirements.
E.g. complicated bake wares, cell phone cover

General Information			
Features	Good Tear Strength		
Uses	Cove Base		
	Household Goods		
	Non-specific Food Applications		
Appearance	Translucent		
Physical	Nominal Value	Unit	Test Method
Density	1.03 to 1.11	g/cm ³	ASTM D1505
Molding Shrinkage - Flow	3.2 to 3.7	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	30 to 34		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Set	< 8	%	ASTM D412
Tensile Strength (Yield)	> 8.00	MPa	ASTM D412
Tensile Elongation (Break)	> 700	%	ASTM D412
Tear Strength	> 20.0	kN/m	ASTM D624
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+16	ohms·cm	ASTM D257
Dielectric Strength	> 22	kV/mm	ASTM D149

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT