

ELASTOSIL® N 2199

Silicone

Wacker Chemie AG

Message:

Silicone Rubber, RTV-1

Bonding & Sealing, Renewable Energies

Coating of Fabrics and Textiles, Technical Textiles

Bonding & Sealing, Adhesives and Sealants

Technical Textiles, Technical Textiles

Adhesion of Textiles, Technical Textiles

Bonding & Sealing, Mechanical and Plant Engineering

General Information			
Uses	Adhesives		
	Bonding		
	Sealants		
Uncured Properties	Nominal Value	Unit	Test Method
Color	Clear/Transparent		
Density	1.06	g/cm ³	ISO 2811
Skin Forming Time ¹ (23°C)	15.0	min	
Cured Properties	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	30		ISO 868
Tensile Modulus (100% Secant)	1.00	MPa	ISO 37
Tensile Strength	2.50	MPa	ISO 37
Tensile Elongation at Break	350	%	ISO 37
NOTE			
1.	50% R.H		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT