# THERMOLAST® M TM4MED (Series: MC/tl)

#### Thermoplastic Elastomer

#### **KRAIBURG TPE**

#### Message:

The MC/tl Series is your material solution for applications requiring basic medical approvals such as ISO 10993-5. The compounds are produced exclusively by a special medical unit and available in translucent colors.

Typical applications

Flexible Connections

Mouthpieces

Seals

Soft touch

Valves

Material advantages

Adhesion to PP

DMF listed

Excellent compression set

For injection molding and extrusion

Free of animal baseding redients

KRAIBURG TPE Medical service package (description below)

Sterilizable (autoclave 134°C, gammaradiation 2x35 kGy, EtO)

Tested according to ISO 10993-5

General Information					
Features	Autoclave Sterilizable				
	Ethylene Oxide Sterilizable				
	Good Adhesion				
	No Animal Derived Components				
	Radiation Sterilizable				
Uses	Connectors				
	Medical/Healthcare Applications				
	Seals				
	Soft Touch Applications				
	Valves/Valve Parts				
Agency Ratings	DMF 22979				
	ISO 10993 Part 5				
Appearance	Translucent				
Processing Method	Extrusion				
	Injection Molding				
Physical	Nominal Value	Unit	Test Method		
Density	0.880	g/cm³	ISO 1183		
Hardness	Nominal Value	Unit	Test Method		

Shore Hardness (Shore A)	36		ISO 7619
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress <sup>1</sup> (Yield)	8.00	MPa	ISO 37
Tensile Elongation <sup>2</sup> (Break)	800	%	ISO 37
Tear Strength <sup>3</sup>	12	kN/m	ISO 34-1
Compression Set <sup>4</sup>			ISO 815
23°C, 72 hr	16	%	
70°C, 24 hr	26	%	
100°C, 24 hr	43	%	
Extrusion	Nominal Value	Unit	
Drying Temperature	60.0 to 80.0	°C	
Drying Time	2.0 to 4.0	hr	
Cylinder Zone 1 Temp.	160	°C	
Cylinder Zone 2 Temp.	180	°C	
Cylinder Zone 3 Temp.	200	°C	
Die Temperature	200 to 230	°C	
NOTE			
1.	Type S2, 200 mm/min		
2.	Type S2, 200 mm/min		
3.	Method Bb, Angle (Nicked)		
4.	Method A		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

