

Tufpet PBT G2930

Polybutylene Terephthalate
Mitsubishi Rayon America Inc.

Message:

Tufpet PBT G2930 is a Polybutylene Terephthalate (PBT) material filled with 30% glass fiber. It is available in North America for injection molding. Important attributes of Tufpet PBT G2930 are:
Flame Rated
Chemical Resistant
Good Dimensional Stability
Good Processability
Heat Resistant

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Features	Good Chemical Resistance		
	Good Dimensional Stability		
	Good Electrical Properties		
	Good Moldability		
	High Gloss		
	High Heat Resistance		
	Low to No Water Absorption		
	Low Warpage		
	Tracking Resistant		
Appearance	Natural Color		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.68	g/cm³	ASTM D792
Water Absorption (Saturation, 23°C)	0.080	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	80.4	MPa	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus	8830	MPa	ASTM D790
Flexural Strength	118	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	59	J/m	ASTM D256
Unnotched Izod Impact	200	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	215	°C	
1.8 MPa, Unannealed	180	°C	

RTI Elec			UL 746
0.740 mm	75.0	°C	
1.50 mm	75.0	°C	
3.18 mm	75.0	°C	
RTI Imp			UL 746
0.740 mm	75.0	°C	
1.50 mm	75.0	°C	
3.18 mm	75.0	°C	
RTI Str			UL 746
0.740 mm	75.0	°C	
1.50 mm	75.0	°C	
3.18 mm	75.0	°C	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	5.0E+18	ohms·cm	ASTM D257
Dielectric Strength	22	kV/mm	ASTM D149
Arc Resistance	126	sec	ASTM D495
Comparative Tracking Index (CTI)	450	V	UL 746
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.740 mm	V-1		
1.50 mm	V-0		
3.18 mm	V-0		
Injection	Nominal Value	Unit	
Drying Temperature	140	°C	
Drying Time	2.0	hr	
Rear Temperature	230 to 303	°C	
Middle Temperature	230 to 303	°C	
Front Temperature	230 to 303	°C	
Mold Temperature	40.0 to 100	°C	
Injection Pressure	81.4	MPa	
Screw Speed	80	rpm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT