

Carbotex K-20MRA

Polycarbonate
Kotec Corporation

Message:

Carbotex K-20MRA is a Polycarbonate (PC) product. It can be processed by injection molding and is available in Africa & Middle East, Europe, Latin America, or North America.

Characteristics include:

- Flame Rated
- Good Mold Release
- High Flow
- Mold Release Agent

General Information			
UL YellowCard	E146413-100218313		
Additive	Mold Release		
Features	General Purpose		
	Good Mold Release		
	High Flow		
Uses	General Purpose		
Appearance	Clear/Transparent		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	20	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.50 to 0.70	%	ASTM D955
Water Absorption (23°C, 24 hr)	< 0.20	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	63.0	MPa	ASTM D638
Tensile Elongation (Break)	120	%	ASTM D638
Flexural Modulus	2160	MPa	ASTM D790
Flexural Strength	85.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	740	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	131	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+16	ohms · cm	ASTM D257
Dielectric Strength (1.60 mm)	20	kV/mm	ASTM D149
Dielectric Constant (1 MHz)	2.90		ASTM D150

Dissipation Factor (1 MHz)	9.0E-3		ASTM D150
Arc Resistance	110	sec	ASTM D495
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.400 mm)	V-2		UL 94
Optical	Nominal Value	Unit	Test Method
Refractive Index	1.580		ASTM D542
Transmittance (3000 μm)	89.0	%	ASTM D1003
Haze (3000 μm)	< 1.0	%	ASTM D1003

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

