

LNP™ THERMOCOMP™ RZ0069 compound

Polyamide 66

SABIC Innovative Plastics

Message:

LNP THERMOCOMP RZ0069 is a compound based on Nylon 66 resin containing Glass Fiber, Flame Retardant, Milled Glass. Added features of this material include: Flame Retardant.

Also known as: LNP* THERMOCOMP* Compound RF-1006 FR M

Product reorder name: RZ0069

General Information			
Filler / Reinforcement	Grinding Glass/Fiberglass		
Features	Flame retardancy		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.57	g/cm ³	ASTM D792
Molding Shrinkage - Flow (24 hr)	1.2	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹	5250	MPa	ASTM D638
Tensile Strength (Break)	52.4	MPa	ASTM D638
Tensile Elongation (Break)	1.8	%	ASTM D638
Flexural Modulus	5210	MPa	ASTM D790
Flexural Strength	96.5	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	32	J/m	ASTM D256
Unnotched Izod Impact (23°C)	280	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 3.20 mm)	146	°C	ASTM D648
NOTE			
1.	50 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT