# OpteSTAT<sup>™</sup> NC PES 6010

### Polyethersulfone

**Ovation Polymers Inc.** 

#### Message:

OpteSTAT<sup>™</sup> master batches are Ovation Polymers' line of nano-compounds based on carbon nanotubes. Our proprietary dispersion technology debundles and disentangles carbon nanotubes without compromising their integrity. OpteSTAT<sup>™</sup> compounds exhibit good conductivity at minimal nanotube loadings, achieving exceptional cleanliness and physical property retention.

OpteSTAT<sup>™</sup> NC PES 6010 is Polyether Sulfone-based carbon nanotube compound. The material resistivity can be tailored to the application, while retaining the physical and thermal properties of the base polymer.

Target applications include components of disk drives, business machines or other electronic assemblies where ESD control is required while retaining exceptional cleanliness, dimensional control and physical properties.

General Information			
Filler / Reinforcement	Carbon Nano		
Features	Clean/High Purity		
	Conductive		
	ESD Protection		
	Good Dimensional Stability		
	Good Electrical Properties		
Uses	Business Equipment		
	Computer Data Storage		
	Electrical Parts		
	Masterbatch		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.36	g/cm³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus <sup>1</sup>	2400	МРа	ASTM D638
Tensile Strength <sup>2</sup> (Yield)	90.0	МРа	ASTM D638
Flexural Modulus <sup>3</sup> (50.0 mm Span)	2600	МРа	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	80	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 3.20 mm)	146	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+4 to 1.0E+7	ohms	ASTM D257
NOTE			
1.	50 mm/min		
2.	50 mm/min		
3.	1.3 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

