

# Jam PE 26560

Linear Low Density Polyethylene

Jam Petrochemical Company

## Message:

Jam PE 26560 is a Linear Low Density Polyethylene product. It can be processed by injection molding and is available in Africa & Middle East.

Characteristics include:

Butene Comonomer

Fast Molding Cycle

General Information			
Features	Butene Comonomer		
	Fast Molding Cycle		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.926	g/cm³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	60	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield, Compression Molded	15.0	MPa	
Break, Compression Molded	15.0	MPa	
Tensile Elongation (Break, Compression Molded)	10	%	ASTM D638
Flexural Modulus (Compression Molded)	580	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	No Break		ASTM D256A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	52.0	°C	ASTM D648
Vicat Softening Temperature	85.0	°C	ASTM D1525

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT