

Flontech® FT-903-ST

Polytetrafluoroethylene

Guarniflon S.p.A. - Flontech Division

Message:

100% virgin PTFE

General Information			
Appearance	White		
Forms	Powder		
Physical	Nominal Value	Unit	Test Method
Apparent Density	0.30	g/cm ³	ASTM D4894
Melt Mass-Flow Rate (MFR)	1.5	g/10 min	ASTM D1238
Water Absorption (Equilibrium)	< 0.10	%	Internal Method
Particle Size Distribution			Internal Method
at 10%	700	nm	
at 50%	2000	nm	
at 90%	5000	nm	
Specific Surface Area	3.0	m ² /g	ASTM D4567
Thermal	Nominal Value	Unit	Test Method
Melting Temperature	333	°C	ASTM D4591

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

