

# I. Stern 1335

Polypropylene Homopolymer  
I. STERN & CO. INC.

Message:

1335 - Prime Homopolymer Polypropylene  
Features  
Excellent flow characteristics  
FDA  
Good mold release  
Low odor and taste  
Applications  
closures  
housewares  
small appliances  
toys

General Information			
Features	Good Mold Release		
	High Flow		
	Homopolymer		
	Low to No Odor		
	Low to No Taste		
Uses	Appliances		
	Closures		
	Household Goods		
	Toys		
Agency Ratings		FDA Unspecified Rating	
Physical	Nominal Value	Unit	Test Method
Density	0.900	g/cm <sup>3</sup>	ASTM D1505
Melt Mass-Flow Rate (MFR)	35	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength <sup>1</sup> (Yield)	35.9	MPa	ASTM D638
Tensile Elongation <sup>2</sup> (Break)	11	%	ASTM D638
Flexural Modulus - 1% Secant <sup>3</sup>	1380	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	27	J/m	ASTM D256
NOTE			
1.	51 mm/min		
2.	51 mm/min		
3.	1.3 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

