

EnCom LG ABS 40

Acrylonitrile Butadiene Styrene

EnCom, Inc.

Message:

Low Gloss ABS

General Information	
Features	Low Gloss
Uses	Automotive Applications
	Business Equipment
	General Purpose
	Thin-walled Parts
Appearance	Black
Forms	Pellets
Processing Method	Injection Molding
	Profile Extrusion

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.05	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.40 to 0.80	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	42.7	MPa	ASTM D638
Flexural Modulus	2410	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	190	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	91.7	°C	
1.8 MPa, Unannealed	83.3	°C	
CLTE - Flow	7.5E-5	cm/cm/°C	ASTM D696
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
1.57 mm	HB		
3.18 mm	HB		
Injection	Nominal Value	Unit	
Drying Temperature	82.2 to 93.3	°C	
Drying Time	2.0 to 4.0	hr	
Drying Time, Maximum	7.0	hr	
Suggested Max Moisture	0.15	%	

Rear Temperature	188 to 232	°C
Middle Temperature	204 to 246	°C
Front Temperature	218 to 260	°C
Nozzle Temperature	218 to 274	°C
Processing (Melt) Temp	218 to 274	°C
Mold Temperature	48.9 to 76.7	°C
Back Pressure	0.172 to 0.689	MPa
Screw Speed	25 to 75	rpm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

