

NORYL™ FE1740PW resin

Polyphenylene Ether + PS

SABIC Innovative Plastics Europe

Message:

Noryl* FE1740PW Polyphenylene Oxide (PPO) + Polystyrene (PS) resin is a 40 % Glass Reinforced, injection moldable grade with improved hydrolytic stability and with a Tensile Modulus >11000 MPa; this grade has been developed for fluid engineering applications where higher static stiffness is required. Noryl* FE1740PW has been certified for potable water applications up to 85C in Europe and North America in limited colours.

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 40% filler by weight		
Features	Rigid, good		
Uses	Potable water application		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.40	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/5.0 kg)	10	g/10 min	ASTM D1238
Melt Volume-Flow Rate (MVR) (300°C/10.0 kg)	20.0	cm ³ /10min	ISO 1133
Molding Shrinkage - Flow (3.20 mm)	0.090 - 0.15	%	Internal method
Water Absorption			ISO 62
Saturated, 23°C	0.20	%	ISO 62
Equilibrium, 23°C, 50% RH	0.060	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	13800	MPa	ASTM D638
--	11300	MPa	ISO 527-2/1
Tensile Strength			
Fracture ²	165	MPa	ASTM D638
Fracture	155	MPa	ISO 527-2/5
Tensile Elongation			
Fracture ³	1.8	%	ASTM D638
Fracture	1.8	%	ISO 527-2/5
Flexural Modulus			
50.0mm span ⁴	11700	MPa	ASTM D790
-- ⁵	9500	MPa	ISO 178
Flexural Stress			
--	195	MPa	ISO 178
Fracture, 50.0mm span ⁶	225	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength ⁷ (23°C)	30	kJ/m ²	ISO 179/1eU

Notched Izod Impact			ASTM D256
-30°C	90	J/m	ASTM D256
23°C	110	J/m	ASTM D256
Unnotched Izod Impact Strength ⁸			ISO 180/1U
-30°C	30	kJ/m ²	ISO 180/1U
23°C	30	kJ/m ²	ISO 180/1U
Instrumented Dart Impact (23°C, Total Energy)			ASTM D3763
	18.0	J	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, unannealed, 3.20mm	148	°C	ASTM D648
1.8 MPa, unannealed, 64.0mm span ⁹	147	°C	ISO 75-2/Af
Vicat Softening Temperature			
--	151	°C	ASTM D1525 ¹⁰
--	152	°C	ISO 306/B50
--	161	°C	ISO 306/B120
Linear thermal expansion coefficient			ISO 11359-2
Flow: -40 to 40°C	2.0E-5	cm/cm/°C	ISO 11359-2
Lateral: -40 to 40°C	7.0E-5	cm/cm/°C	ISO 11359-2
Injection	Nominal Value	Unit	
Drying Temperature	100 - 120	°C	
Drying Time	2.0 - 4.0	hr	
Suggested Max Moisture	0.020	%	
Hopper Temperature	60.0 - 80.0	°C	
Rear Temperature	250 - 270	°C	
Middle Temperature	270 - 290	°C	
Front Temperature	290 - 310	°C	
Nozzle Temperature	280 - 300	°C	
Processing (Melt) Temp	280 - 300	°C	
Mold Temperature	80.0 - 120	°C	
NOTE			
1.	5.0 mm/min		
2.	Type 1, 5.0 mm/min		
3.	Type 1, 5.0 mm/min		
4.	1.3 mm/min		
5.	2.0 mm/min		
6.	1.3 mm/min		
7.	80*10*4 sp=62mm		
8.	80*10*4		
9.	80*10*4 mm		
10.	标准 B (120°C/h), 载荷2 (50N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

