

Veroplas SER20

Acrylonitrile Butadiene Styrene

PlastxWorld Inc.

Message:

Veroplas SER20 is an Acrylonitrile Butadiene Styrene (ABS) product. It is available in Europe or North America.

Characteristics include:

- Flame Rated
- Flame Retardant
- Good Processability

General Information			
UL YellowCard	E315545-100118263		
Features	Flame Retardant		
	General Purpose		
	Good Moldability		
Uses	General Purpose		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.18	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/3.8 kg)	13	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.40 to 0.60	%	ASTM D955
Water Absorption (24 hr)	0.30	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	114		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	41.4	MPa	ASTM D638
Flexural Modulus	2140	MPa	ASTM D790
Flexural Strength	75.8	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	220	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	82.2	°C	ASTM D648
Vicat Softening Temperature	90.0	°C	ASTM D1525
CLTE - Flow	8.6E-5	cm/cm/°C	ASTM D696
RTI Imp	70.0	°C	UL 746
RTI Str	70.0	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	2.4E+15	ohms · cm	ASTM D257
Dielectric Strength (1.59 mm)	35	kV/mm	ASTM D149
Arc Resistance (3.05 mm)	10.0	sec	ASTM D495

Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.0600 mm, ALL	V-1		
0.0800 mm, ALL	V-0		
0.100 mm, ALL	5V		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
 Phone: +86 13424755533
 Email: sales@su-jiao.com
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT