

Toler EVA 286

Ethylene Vinyl Acetate Copolymer
Toler Chemical, Inc

Message:

286 provides a flexible base resin for hot melt adhesives, sealants and coatings. 286 exhibits wax compatibility and can be formulated into a wide range of systems. This product promotes higher temperature performance as well as adhesion to a variety of substrates. 286 contains a stabilizing additive package and can also be used in compounded products where high filler loadings are required.

General Information	
Additive	Unspecified Stabilizer
Features	Copolymer
	Good Adhesion
	Good Stability
	Good Thermal Stability
Uses	Adhesives
	Coating Applications
	Compounding
	Sealants

Physical	Nominal Value	Unit	Test Method
Density	0.948 to 0.952	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR)	5.0 to 7.0	g/10 min	ASTM D1238
Vinyl Acetate Content	28.0	wt%	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	75 to 80		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus - 1% Secant	17.2 to 20.0	MPa	ASTM D638
Tensile Strength (Break)	15.2	MPa	ASTM D638
Tensile Elongation (Break)	730 to 780	%	ASTM D638
Thermal	Nominal Value	Unit	Test Method
Melting Temperature	71.0	°C	ASTM D3417
Ring and Ball Softening Point	140 to 145	°C	ASTM E28

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

