

# MAJORIS AG200E - 8229

High Density Polyethylene

AD majoris

## Message:

MAJORIS AG200E - 8229 is a 20% glass fibre reinforced polyethylene high density compound intended for injection moulding and extrusion profiles. The product is available in black (MAJORIS AG200E - 8229) and natural (MAJORIS AG200E) but other colours can be provided on request.

## APPLICATIONS

MAJORIS AG200E - 8229 is intended for components which require good impact strength, rigidity, dimensional stability.

Suitable applications are:

Electrical tool and appliance components

Miscellaneous automotive technical items

Profile

General Information	
Filler / Reinforcement	Glass fiber reinforced material, 20% filler by weight
Features	Good dimensional stability
	High density
	Impact resistance, good
	Recyclable materials
	Medium hardness
Uses	Electrical/Electronic Applications
	Power/other tools
	Home appliance components
	Application in Automobile Field
	Profile
Appearance	Black
	Available colors
	Natural color
Forms	Particle
Processing Method	Profile extrusion molding
	Injection molding

Physical	Nominal Value	Unit	Test Method
Density	1.04	g/cm <sup>3</sup>	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/5.0 kg)	0.50	g/10 min	ISO 1133
Molding Shrinkage			
Vertical flow direction: 2.00mm	0.70	%	
Flow direction: 2.00mm	0.40	%	
Mechanical	Nominal Value	Unit	Test Method

Tensile Modulus	3150	MPa	ISO 527-2/1
Tensile Stress (Yield)	43.0	MPa	ISO 527-2/50
Flexural Modulus <sup>1</sup>	3150	MPa	ISO 178
Flexural Stress	67.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	24	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	66	kJ/m <sup>2</sup>	ISO 179/1eU
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Rear Temperature	200 - 220	°C	
Processing (Melt) Temp	210 - 250	°C	
Mold Temperature	30.0 - 50.0	°C	
Injection Rate	Moderate		
Injection instructions			
Holding pressure: 50 to 70% of the injection pressure			
NOTE			
1.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

