

# Hifax X M2 U16 C11544

Polypropylene Homopolymer  
LyondellBasell Industries

Message:

Hifax X M2 U16 is a 20% talc filled PP homopolymer compound, with outstanding stiffness, good flowability and very good UV resistance. This product is also available in other colors, new colors can be developed depending on customer requirements. For regulatory compliance information, see Hifax X M2 U16 C11544 Product Stewardship Bulletin (PSB) and Safety Data Sheet (SDS). This grade is not intended for medical, pharmaceutical, food and drinking water applications.

General Information			
Filler / Reinforcement	Talc filler, 20% filler by weight		
Features	Rigidity, high		
	Rigid, good		
	Homopolymer		
	Good UV resistance		
	Good liquidity		
	Good color stability		
	Good wear resistance		
	Excellent appearance		
Uses	Application in Automobile Field		
	Automotive exterior parts		
Appearance	Available colors		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.05	g/cm <sup>3</sup>	ISO 1183/A
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	12	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus <sup>1</sup> (23°C)	2700	MPa	ISO 178/A
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	2.5	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	34	kJ/m <sup>2</sup>	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	110	°C	ISO 75-2/B
NOTE			
1.	1.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT