

Nymax™ 1308 A HS Black 13

Polyamide 66

PolyOne Corporation

Message:

Nymax® Series nylon 6/6 composite materials are specially developed for excellent performance in a wide range of applications. According to different grade requirements, these materials include a series of fillers, steel grade glass materials and impact modifiers, which are easier to process in most standard thermoplastic processing equipment.

General Information			
Additive	Impact modifier heat stabilizer		
Features	Impact modification Thermal Stability General		
Uses	Industrial application Architectural application field Application in Automobile Field General Consumer goods application field		
Appearance	Black		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.11	g/cm ³	ASTM D792
Molding Shrinkage - Flow	1.6	%	ASTM D955
Water Absorption (24 hr, 3.18 mm)	1.2	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Break)	59.3	MPa	ASTM D638
Tensile Elongation ² (Break)	45	%	ASTM D638
Flexural Modulus	2000	MPa	ASTM D790
Flexural Strength	82.7	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm, Injection Molded)	150	J/m	ASTM D256A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 3.18 mm)	62.0	°C	ASTM D648
Melting Temperature	254	°C	ASTM D789

Additional Information

模制试验条:模制时干燥

NOTE

- | | |
|----|--------------------|
| 1. | Type 1, 5.1 mm/min |
| 2. | Type 1, 5.1 mm/min |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

