# Mylar® A (1400 guage)

### Polyethylene Terephthalate

DuPont Teijin Films U.S.

#### Message:

Mylar Type A films have balanced tensile properties and excellent resistance to moisture and most chemicals. They can withstand temperature extremes from -94 to 302°F. Mylar does not become brittle with age under normal conditions, because it contains no plasticizers.

General Information				
UL YellowCard	E93687-252918			
Features	General Purpose			
	Good Adhesion			
	Good Chemical Resistance			
	Good Processability			
	Good Thermal Stability			
	Good Toughness			
	Moisture Resistant			
	Non-Smooth Surface Fini	sh		
Uses	Carbon Ribbons			
	Film 			
	Labels			
	Liners			
	Protective Coverings			
	Таре			
Appearance	Translucent			
Forms	Film			
Physical	Nominal Value	Unit	Test Method	
Density	1.39	g/cm³	ASTM D1505	
Molding Shrinkage			ASTM D955	
Flow: 0.350 mm	1.3	%		
Across Flow: 0.350 mm	0.80	%		
Films	Nominal Value	Unit	Test Method	
Film Thickness - Tested	350	μm		
Tensile Strength			ASTM D882	
MD : Yield	179	MPa		
TD : Yield	172	MPa		
Tensile Elongation			ASTM D882	
MD : Break	170	%		
TD : Break	170	%		

Optical	Nominal Value	Unit	Test Method
Haze	46	%	ASTM D1003

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



Page 2