

REVODE 190

Polylactic Acid
Zhejiang Hisun Biomaterials Co.,Ltd

Message:
Hisun PLA---REVODE190 is a thermoplastic resin derived from annually renewable resources

General Information			
Features	Renewable Resource Content		
Appearance	Clear/Transparent Opaque		
Physical	Nominal Value	Unit	Test Method
Density	1.20 to 1.30	g/cm ³	Internal Method
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	2.0 to 10	g/10 min	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	> 50.0	MPa	Internal Method
Tensile Strain (Break)	> 3.0	%	Internal Method
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength	3.0 to 5.0	kJ/m ²	Internal Method
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature	60.0 to 63.0	°C	Internal Method
Melting Temperature	170 to 180	°C	Internal Method

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China


WECHAT