

# REPOL® B220MN

Polypropylene Impact Copolymer

Reliance Industries Limited

## Message:

Repol B220MN is recommended for use in Injection Moulding processes where high flow and medium impact strength are required. It is an ideal material to use in rigid packaging, automotive components, housewares and appliances parts. Repol B220MN contains nucleating agent.

General Information			
UL YellowCard	E239367-230527		
Additive	Nucleating Agent		
Features	Food Contact Acceptable		
	High Flow		
	Medium Impact Resistance		
	Nucleated		
Uses	Appliance Components		
	Automotive Applications		
	Rigid Packaging		
Agency Ratings	FDA 21 CFR 177.1520		
	IS 10909		
	IS 10910		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	22	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength <sup>1</sup> (Yield, Injection Molded)	25.0	MPa	ASTM D638
Tensile Elongation <sup>2</sup> (Yield, Injection Molded)	8.0	%	ASTM D638
Flexural Modulus - 1% Secant (Injection Molded)	1200	MPa	ASTM D790A
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, Injection Molded)	80	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed, Injection Molded)	105	°C	ASTM D648
NOTE			
1.	Type I, 50 mm/min		
2.	Type I, 50 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533  
Email: sales@su-jiao.com  
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

