

# Petrothene® LT493721

High Density Polyethylene  
LyondellBasell Industries

Message:

.Petrothene LT493721 exhibits an enhanced balance of stiffness and environmental stress crack resistance. Typical applications include bottles for detergents, household and industrial chemicals. This product is formulated with synthetic antistat.

General Information			
Additive	Antistatic		
Features	Food Contact Acceptable		
	Good Stiffness		
	High ESCR (Stress Crack Resist.)		
Uses	Blow Molding Applications		
	Bottles		
	Household Goods		
	Industrial Applications		
Agency Ratings	FDA 21 CFR 177.1520		
Processing Method	Blow Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.949	g/cm <sup>3</sup>	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.34	g/10 min	ASTM D1238
Environmental Stress-Cracking Resistance (50°C, 100% Igepal CO-630, F50)	300	hr	ASTM D1693
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	63		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	24.4	MPa	ASTM D638
Tensile Elongation (Break)	1300	%	ASTM D638
Flexural Modulus	1080	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Tensile Impact	71.5	J/cm	ASTM D1822
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	65.0	°C	ASTM D648
Brittleness Temperature	< -76.0	°C	ASTM D746
Vicat Softening Temperature	124	°C	ASTM D1525

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT