

RTP 201.3 H HS

Polyamide 66

RTP Company

Message:

Warning: The status of this material is 'Commercial: Limited Issue'
The data for this material has not been recently verified.
Please contact RTP Company for current information prior to specifying this grade.

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 13% filler by weight		
Additive	Impact modifier		
	heat stabilizer		
	Lubricant		
Features	Impact modification		
	Thermal Stability		
	Lubrication		
RoHS Compliance	Contact manufacturer		
Appearance	Black		
	Natural color		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.18	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.50	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.90	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	4480	MPa	ASTM D638
Tensile Strength	83.0	MPa	ASTM D638
Tensile Elongation (Break)	7.0	%	ASTM D638
Flexural Modulus	3790	MPa	ASTM D790
Flexural Strength	124	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.18 mm)	160	J/m	ASTM D256
Unnotched Izod Impact (3.18 mm)	850	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	238	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method

Volume Resistivity	1.0E+14	ohms·cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.59 mm, Values per RTP Company testing.)	HB		UL 94
Additional Information			
Molding Shrinkage, Linear-Flow, ASTM D955, 6.35mm: 7mm/m.			
Injection	Nominal Value	Unit	
Drying Temperature	79.4	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.20	%	
Suggested Max Regrind	20	%	
Rear Temperature	274 - 288	°C	
Middle Temperature	274 - 288	°C	
Front Temperature	274 - 288	°C	
Mold Temperature	66.0 - 93.0	°C	
Injection Pressure	103 - 138	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

