

Dryflex® A2 602709

Styrene Ethylene Butylene Styrene Block Copolymer

ELASTO

Message:

Dryflex A thermoplastic elastomer (TPE) bondable grades, primarily based on SBS and SEBS, increase freedom of design and open up a vast range of application opportunities.

It used to be a complex and costly affair producing details made of thermoplastics that showed soft-touch qualities or had integrated seals. With Dryflex A TPEs, since the materials are bonded together at the production stage, no separate primer or adhesive is needed. This makes the process faster and more cost-effective than if the two parts were assembled together after each had been produced separately, or bonded mechanically, which often requires some modification to the design.

Primarily a TPE is used as the soft component. Dryflex A bondable grades can be co-extruded or overmoulded with a variety of engineering plastics. Dryflex A grades are available in black or natural and can easily be coloured. These thermoplastic elastomers form excellent bonds onto PP, PE, PA, ABS, PC, PS, PMMA, ASA, SAN and their blends. Polyamides and ABS may be either reinforced or non-reinforced yet still bond extremely well to Dryflex. It is easy to achieve excellent bonding to PP, even using standard TPE materials, while other thermoplastics require some modification of the TPE material to optimise bonding.

General Information			
Features	Bondability		
	Food Contact Acceptable		
	Good Adhesion		
	Good Chemical Resistance		
Appearance	Black		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.16	g/cm³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	70		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
--	6.00	MPa	
100% Strain	3.00	MPa	
300% Strain	5.00	MPa	
Tensile Elongation (Break)	500	%	ASTM D638
Elastomers	Nominal Value	Unit	Test Method
Tear Strength	34.0	kN/m	ASTM D624
Thermal	Nominal Value	Unit	
Service Temperature	-50 to 125	°C	
Peel Force	Cohesive		ASTM D903

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

